

210011

NC Clear Sealer 011

Transparent Nitrocellulose Sealer

**FEATURES**

Properties:	Quick drying	Very easy sanding	High covering power
Recommended use:	Rustic furnitue	Indoor woodwork	Assembled furniture and chairs
Application method:	Spray Gun	Airmix gun	
Recommended Hardeners:		1	
Recommended solvents:	520201	520204 in summer	540414 anti-blooming; paint brush

**AVAILABLE GLOSSES**


**TYPICAL PROPERTIES (25 °C)**

Supply Viscosity, DIN4	44 - 64 s		
Density (kg/L)	0.940 - 0.970		
VOC content (%w)	59.128		
Solid content ( %)	37 - 41		

**GENERAL FEATURES**

Preparation			
Dust -free drying of 120 g/m <sup>2</sup>	10 min		
Touch-free drying of 120 g/m <sup>2</sup>	20 min		
Stackable	After 8 h		
Sanding / Repainting	3 - 4 h		
Recommended Weight (g/m <sup>2</sup> )	140 - 160		

**SUBSTRATE PREPARATION**

Apply on solid, plated wood or particleboard. It is necessary to sand the surface with 180-220 grit paper and make sure that the substrate is completely clean of dust, dry and free of any contaminant (silicone, grease, remains of varnish.. )

**APPLICATION ADVICE**

The type and quantity of solvent recommended are a guide, it depends on the application system and the environmental conditions.

Generally thin with 15% 520201 Solvent 201 Nitro

At high temperatures or humidity addition of 5 - 10% of 520204 Solvent 204 Retardant Medium or 540414 Solvent 414 Retardant is recommended.

Application	% Thinner	Nozzles	Air Pressure ( bar)	Pump Pressure ( bar)
Spray Gun	10 - 20	2 - 2.5	2.5 - 3	

**PRECAUTIONS**

Mix properly before using.

We recommend to apply at 15 - 25 °C and 50 -75% relative humidity.

Paint residues must be removed according to current regulations.

With regard to the danger and toxicity of this product before using it, we advise you to read its MSDS

Expiry date: 1 year

**ADDITIVES**

Action	ADD	Dosage %	grams per 20 L can
Anti-Silicone Additive	980066 Anti- Silicone Additive 066	0.5-5 %	100- 1000

**Note:** the aforementioned data and the advices we give verbally, in writing or through tests, have been carried out following our loyal knowledge and mind, nevertheless they are considered as mere advices and indications without any obligation, and also with regard to the possible third party industrial property rights. Our advice does not exempt you from doing tests to the indications we may give you or to the products we may provide you, in order to check if these products are the suitable for the purposes indicated. The application, use and transformation of our products and of the products you manufacture under our technical advice will be made out of our vigilance and therefore will be of your sole responsibility. The sale of our products is under our Selling and Delivery General Conditions. //

version 1, 03/03/2017

**VALRESA.** Polígono Industrial Reva  
 Avda.dels Gremis, s/n Sector 13  
 Riba-Roja de Turia Valencia E46394  
 ESPAÑA Tel. 96 1669560